



检测报告

TEST REPORT


报告编号: 2017010086-1 b
Report No.:

委托单位: 广州市华年新材料科技有限公司
Customer: GuangZhou HuaNian new material technology CO., LTD.

地址: 广州市荔湾区芳村大道西逸彩路大鹏街7号二层
Customer Add.: Guangzhou Liwan District Fangcun West Covent Garden Dapeng Road on the 7th floor

收样日期: 2017-10-18
Date of Sample Received: 2017-10-18

检测地址: 广东省广州市先烈中路100号大院34号楼
Address for Test: Building 34, No.100, Xianlie Middle Road, Guangzhou, Guangdong

编制: 
Organizer:

审核: 
Checker:

批准: 
Authorized signatory:

签发日期: 2017-10-30
Date for Reporting: 2017-10-30





检测报告

TEST REPORT

样品名称: PVC 表印水墨 报告编号: 2017010086-1 b
 Sample Name: PVC table printing water-based ink Report No.:
 样品批号: 2017.10.17 检测日期: 2017-10-18 至 2017-10-30
 Sample Lot No./Batch No.: Testing Period: 18-Oct to 30-Oct
 样品外观: 液体 样品数量: 300mL
 Sample Appearance: Liquid Sample Quantity:

分析检测结果

Test Results

分析项目 Item	检测结果 Result		计量单位 Unit	检测方法 Method
	10min	24h		
VOCs	0.020	0.047	g/m ³	GB/T 18883-2002 附录C
乙醇 Ethanol	0.020	0.047	g/m ³	
以下空白 BLANK BELOW				
备注 Note	样品经质谱检测, 10min、24h均未检出其余VOCs, 乙醇占VOCs总量的100%。 The samples were detected by mass spectrometry. The remaining VOCs was not detected in 10min and 24h, and the ethanol accounted for 100% of VOCs. 在30m ³ 的试验舱中, 放入样品, 40℃水浴加热, 分别于10min及24h采样, 测试乙醇释放量。 In a sealed box(the volume of it is 30m ³), heating sample at 40℃ water bath, then determinate the concentration before and after treated by the sample time.			

检测
 报告专用
 (2)